



CLIENT:

| | |
|---------------|---|
| Company: | Turf Distributors |
| Address: | 4252 Rionedo Road Temecula, CA 92590 |
| Requested By: | Dillon Georgian |

TEST MATERIAL:

| | |
|-------------------------|--------------------------------------|
| Date Material Received: | April 14, 2020 |
| Material Type: | Synthetic Turf |
| Material Condition: | Excellent, New |
| Material ID: | Platinum Putt |
| Infill: | 2.5 lbs/ft ² 60 Grit Sand |

TESTING METHODS REQUESTED:

| | | | |
|--|-----------------|--------------|--|
| Testing Services, Inc was instructed by the client to perform the following testing: | | | |
| Standard: | FIFA Section 17 | Test Method: | Procedure for Simulated Mechanical Abrasion |
| Standard: | EN 15336 | Test Method: | Surface for Sports Area, Exposure for Synthetic Turf to Simulated Wear (LiSport) |

SAMPLING PLAN:

| | |
|---|-----------|
| Sampling Date: | 4/14/2020 |
| <ul style="list-style-type: none"> Specimen sampling is performed in the sampling department at TSI. The sampling size of specimens is determined by the test method requirements. In the event a specific sampling size is not called for, a determination will be made based on previous testing experience, and approved for use by an authorized manager. All samples are subjected to the outside environmental conditions of temperature and relative humidity. Sample requiring pre-determined exposure to specified environmental conditions based on a specific test method, take place in the departments in which they are tested | |

TEST EQUIPMENT:

| | |
|--------------|----------------------------|
| Wear Tester: | Deltac Manual 1.2m LiSport |
| Model #: | Y2017 1701003 |
| Date of Mfg: | 1/2017 |
| Dimensions: | 3070mm X 1300mm |

PRINCIPLE:

This procedure simulates high levels of athletic use of the synthetic turf in an accelerated period of time under laboratory conditions. Two studded rollers were traversed to and fro over the infilled turf to produce mechanical action of the surface that occurs during normal use. This report details the effects of this mechanical action as it relates to degradation of the pile fiber.

The client, Artificial Grass Liquidators, commissioned TS to evaluate simulated wear of submitted finished synthetic turf, referenced above, with the use of an infill system.

The results are indicative of mechanical wear only and do not take into account the effects of weathering, uv degradation, or use of the turf outside of competition.

PROCEDURE:

A test specimen, 560mm X 2438mm, was cut from the sample lot to be exposed to mechanical abrasion. The specimen was infilled with above listed infill. The rollers were positioned onto the surface of the system, with the pressure set automatically @ 1kg per cm. All speeds of the machine components were set in accordance with FIFA & CEN standards. The design of the machine ensures that the studs do not repeatedly impact the same spots.

The Lisport was activated for 1,000 cycles. At the end of the 1,000 cycles the pile fiber degradation was graded, a photo and fiber sample were taken.

DEVIATION FROM TEST METHOD:

| |
|--|
| State reason for any deviation from, additions to, or exclusions from test method: |
| None |

CLIENT:

| | |
|---------------|---|
| Company: | Turf Distributors |
| Address: | 4252 Rionedo Road Temecula, CA 92590 |
| Requested By: | Dillon Georgian |

TEST MATERIAL:

| | |
|----------------------------|--------------------------------------|
| Date Material Received: | April 14, 2020 |
| Material Type: | Synthetic Turf |
| Material Condition: | Excellent, New |
| Material ID: | Platinum Putt |
| Infill: | 2.5 lbs/ft ² 60 Grit Sand |
| Measured Tuft Height: | 16mm |
| Average Infill Depth: | 12mm |
| Exposed Tuft Above Infill: | 4mm |

TEST RESULTS:

- A scale of 1 to 5 was used for descriptive evaluation of the pile fibers due to the effect of mechanical wear (Lisport) at each 1,000 cycle interval.
- The following is an explanation of the scale:

| Rating | Description |
|--------|--------------------|
| 1.0 | None or Negligible |
| 2.0 | Slight |
| 3.0 | Moderate |
| 4.0 | Considerable |
| 5.0 | Severe |

- The following was rated using the referenced rating scale: tuft loss, pile flattening, fiber splitting, and infill dispersion.





| # of Cycles | Infill Dispersion | Tuft Loss | Pile Flattening | Fiber Splitting |
|-------------|-------------------|-----------|-----------------|-----------------|
| 1,000 | 2.0 | 1.5 | 3.5 | 1.0 |

CONCLUSION:

Photographs of the overall view of the fibers are provided in the following appendixes.

Infill dispersion and tuft loss was slight for the entire test duration. Fiber splitting was negligible. Pile flattening was very moderate.

APPENDIX A: Camera and Microscopic View of Fibers

| | | |
|--|---|---|
| Prior to any LiSport Exposure |  |  |
| After 1,000 Cycles of LiSport Exposure |  |  |

Uncertainty:
 We undertake all assignments for our clients on a best effort basis. Our findings and judgments are based on the information to us using the latest test methods available. TSI can only ensure the test results for the specific items tested. Unless otherwise noted in the deviations sections of this report, all tests are performed in compliance with stated test method.

Test Report Approval:

Erle Miles, III, Lab Director Testing Services (TSI) LLC

TSI Accreditation:

Our laboratory is accredited by the US Dept. of Commerce, National Institute of Standards and Technology: ISO/IEC 17025:2005. Our code # is: NVLAP 100108-0. TSI is an Organizational Member of ASTM (American Society for Testing and Materials). TSI is a certified independent testing laboratory by the STC (Synthetic Turf Council).



Testing Services (TSI) LLC
 817 Showalter Avenue
 PO Box 1343
 Dalton, GA 30721