



CLIENT:

| | |
|---------------|--|
| Company: | Turf Distributors |
| Address: | 42505 Rionedo Road Temecula, CA 92590 |
| Requested By: | Dillon Georgian |

TEST MATERIAL:

| | |
|-------------------------|----------------|
| Date Material Received: | April 14, 2020 |
| Material Type: | Synthetic Turf |
| Material Condition: | Excellent, New |
| Material ID: | So Natural 70 |

TESTING METHODS REQUESTED:

| | | | |
|--|-----------|--------------|--|
| <i>Testing Services Inc. was instructed by the client to test for the following...</i> | | | |
| Standard: | ASTM G154 | Test Method: | Standard Practice for Operating Fluorescent Light Apparatus for UV Exposure of Non-Metallic Material |

SAMPLING PLAN:

| | |
|---|-----------|
| Sampling Date: | 4/14/2020 |
| <ul style="list-style-type: none"> Specimen sampling is performed in the sampling department at TSI. The sampling size of specimens is determined by the test method requirements. In the event a specific sampling size is not called for, a determination will be made based on previous testing experience, and approved for use by an authorized manager. All samples are subjected to the outside environmental conditions of temperature and relative humidity. Sample requiring pre-determined exposure to specified environmental conditions based on a specific test method, take place in the departments in which they are tested | |

DEVIATION FROM TEST METHOD:

| |
|--|
| State reason for any Deviation from, Additions to, or Exclusions From Test Method. |
| None |

TEST SUMMARY:

| TEST METHOD | TEST DESCRIPTION | TEST RESULTS | | | |
|--------------|----------------------------|--------------------------|--------------------------|-------------------------|-------------------------|
| | | 500 Hours Exposure | 1000 Hours Exposure | 1500 Hours Exposure | 2000 Hours Exposure |
| ASTM G154-16 | QUV Accelerated Weathering | Color: 10 Texture: 10 | Color: 10 Texture: 10 | Color: 9 Texture: 10 | Color: 9 Texture: 10 |

| | | | |
|----------------|---|--|---|
| Change Rating: | 10: Negligible or No Effect 9: Very Slight 8: Slight 6: Moderate 4: Pronounced 2: Severe 0: Very Severe | Test Equipment: QUV/se UVA-340 lamps, 0.77 W/m ² 16 hours UV light @ 60°C 8 hours condensation @ 50°C Light Cycle: Continuous | *Ratings and comments are based on guidelines provided by Q Labs. |
|----------------|---|--|---|

Uncertainty:

We undertake all assignments for our clients on a best effort basis. Our findings and judgments are based on the information to us using the latest test methods available. TSI can only ensure the test results for the specific items tested. Unless otherwise noted in the deviations sections of this report, all tests are performed in compliance with stated test method.

Test Report Approval:

Erle Miles, III, Lab Director Testing Services (TSI) LLC

TSI Accreditation: Our laboratory is accredited by the US Dept. of Commerce, National Institute of Standards and Technology: ISO/IEC 17025:2005. Our code # is: NVLAP 100108-0. TSI is an Organizational Member of ASTM (American Society for Testing and Materials). TSI is a certified independent testing laboratory by the STC (Synthetic Turf Council).

